

Report No: MAT:AUK12S-03674

Issue No: 3


This report replaces all previous issues of report no 'MAT:AUK12S-03674'.

Material Test Report

Client: Oil Technology Australia (Overseas)
 PO Box 139
 Deception Bay
 Queensland
 Australia QLD 4508

Project: Quality Assurance Testing

The test results reported herein are not accredited. Contact the laboratory for further information. Samples are tested as received unless stated otherwise. This report may only be reproduced in full.


 Approved Signatory: Ajit Thapa
 (Quality Supervisor)

Date of Issue: 09/11/12

Sample Details

Sample ID: AUK12S-03674
Client Sample ID: Ray G
Material: NZS - Melter Chip Grade 3
Sample Source: New Zealand Steel - Glenbrook
Site/Sampled From: Glenbrook Quarry Yard Stockpile
Date Sampled: 05/11/2012
Specification: No Specification
Sampled By: Jurie Breytenbach
Sampling Method: As Received - Not Accredited
Date Tested: 07/11/2012
Technician: Ajit Thapa
Sampling Endorsed: No

Test Results

Description	Method	Result	Limits
Adhesion Agent Used	WDSC B301-89T#	Aggbind Exp-75	N/A
Adhesion Agent Dosage [pph]		0.5	N/A
Binder Type		180/200	N/A
Cutter Used			N/A
Cutter Dosage [pph]			N/A
Geological Description of Aggregate			N/A
Material Sieved Between [mm]		13.2 - 9.5mm	N/A
Sample Washed?		Washed	N/A
Test Temperature [°C]		25.0	N/A
Adhesion Set Up Period [hrs]		2.5	N/A
Adhesion Value		91	≥80
T-Value		1.00	≤2

Comments

The laboratory is not accredited for this test.