

**Research and Development Department****Laboratory Reference: RDB10/060*****TEST REPORT***

ATTENTION:

CLIENT:

CLIENT REFERENCE:

PRODUCT:

TEST METHODS USED:

TESTED BY:

**Ray Georgey**

Otech Australia

0.7% Otech AGGBIND-75<sup>®</sup> by massOtech AGGBIND-75<sup>®</sup> liquid adhesion agent

T230 "Resistance to stripping of aggregates and binders"

Irina Holleran 29/06/2010- 06/07/2010

**TEST RESULTS**



<b>Aggregate Condition</b>	<b>Percent Stripped</b>
As Received	0
Clean and Dry	0
Dusty	0
Saturated, Surface Dry	0
Saturated, Surface Wet	0

Test performed using: Chip from Stevenson Quarry  
Chip sieved between 13.2 & 9.5 mm sieves  
180/200 Penetration Bitumen ex NZRC

***This report may not be reproduced except in full***

Disclaimer: These test results apply to the samples as received by the Laboratory. No liability will be accepted by the Laboratory for any misrepresentation with respect to the sampling of material for testing and/or the use of these test results.

**Research and Development Department**



***This report may not be reproduced except in full***

Disclaimer: These test results apply to the samples as received by the Laboratory. No liability will be accepted by the Laboratory for any misrepresentation with respect to the sampling of material for testing and/or the use of these test results.

**Research and Development Department**



***This report may not be reproduced except in full***

Disclaimer: These test results apply to the samples as received by the Laboratory. No liability will be accepted by the Laboratory for any misrepresentation with respect to the sampling of material for testing and/or the use of these test results.

**Research and Development Department**



Report Issued by Irina Holleran (Technical Services Manager): \_\_\_\_\_

Date Issued: 12/07/2010

***This report may not be reproduced except in full***

Disclaimer: These test results apply to the samples as received by the Laboratory. No liability will be accepted by the Laboratory for any misrepresentation with respect to the sampling of material for testing and/or the use of these test results.